

# Dolomite

20x20 - 20x40

Dolomite grigio | 20x20



# Dolomite

20x20 - 20x40

Gres porcellanato smaltato.  
Glazed porcelain gres.



RS001 beige 20x20 | 8"x8" C7




RS006 beige 20x40 | 8"x16" C7



RS002 grigio 20x20 | 8"x8" C7



RS007 grigio 20x40 | 8"x16" C7



RS003 porfido 20x20 | 8"x8" C7



RS008 porfido 20x40 | 8"x16" C7

Made in Italy

HD  
digital inkjet



R10



9 mm

















<0,5% Bla

## Imballi | Packaging

Formato Size cm	Spessore Thickness mm	Pz / collo Pcs / box	m <sup>2</sup> / collo sqmt / box	Sc / plt Bxs / plt	m <sup>2</sup> / plt Sqmt / plt	Kg / m <sup>2</sup> (netto) Kgs / Sqmt (net)	Kg / collo (netto) Kg / box (net)	Kg / plt
20x20	9	28	1,14	64	72,96	18,05	20,58	1345
20x40	9	14	1,14	64	72,96	18,05	20,58	1345

# CARATTERISTICHE TECNICHE

Technical features

 <b>PROXIMA</b> TENDENZE CERAMICHE		UNI EN 14411 G Gruppo Bla		
		Pavimenti e rivestimenti in gres porcellanato Porcelain wall and floor tiles Sol et carreaux de sol et de mur en grès cérame vitrifié Wand- und Bodenfliesen aus Feinsteinzeug		
		Norma Norm	Valori prescritti International standard	Valori medi Average value
	Lunghezza e larghezza Length and width	UNI EN ISO 10545-2	+/- 0,6 %	Conforme In accordance
	Spessore Thickness	UNI EN ISO 10545-2	+/- 5%	Conforme In accordance
	Rettilinearità degli spigoli Straightness	UNI EN ISO 10545-2	+/- 0,5%	Conforme In accordance
	Ortogonalità Rectangularity	UNI EN ISO 10545-2	+/- 0,6 %	Conforme In accordance
	Planarità Warpage	UNI EN ISO 10545-2	+/- 0,5%	Conforme In accordance
	Assorbimento d'acqua Water absorption	UNI EN ISO 10545-3	≤ 0,5 %	Conforme In accordance
	Resistenza alla flessione Breaking strength	UNI EN ISO 10545-4	> 35 N/mm <sup>2</sup>	Conforme In accordance
	Forza di rottura Breaking force	UNI EN ISO 10545-4	spessore ≥ 7,5 mm ≥ 1.300 N	Conforme In accordance
	Resistenza agli sbalzi termici Thermal Shock resistance	UNI EN ISO 10545-9	Nessun Danno No damage	Conforme In accordance
	Resistenza al cavillo Crazing resistance	UNI EN ISO 10545-11	A richiesta Requested	Conforme In accordance
	Resistenza al gelo Frost resistance	UNI EN ISO 10545-12	A richiesta Requested	Conforme In accordance
	Resistenza all'attacco chimico chemical resistance	UNI EN ISO 10545-13	test method available	Conforme In accordance
	Resistenza alle macchie Stain resistance	UNI EN ISO 10545-14	CLASSE 3 min	Conforme In accordance

L'Azienda si riserva la facoltà di modificare in qualunque momento le informazioni e le caratteristiche tecniche illustrate nel presente catalogo, che non sono comunque da ritenersi legalmente vincolanti. Pesi, colori e misure possono subire variazioni tipiche del particolare processo di cottura del materiale ceramico. I colori e le caratteristiche estetiche dei prodotti sono quanto più possibile vicini a quelli reali, nei limiti consentiti dai processi di stampa. Tutti i formati si intendono nominali.

The Company reserves the right, at any time and without prior notice, to change the information and technical characteristics given in this catalogue, none of which are to be considered legally binding. Weights, colours and dimensions are subject to the normal variations resulting from the ceramic ring process. Within the limits of printed material, the colours and aesthetic features of the products illustrated correspond as closely as possible to those of the actual products.

All sizes are to be considered nominal.

AD  
marketing Gtiles  
smalladv.com

graphic project  
smalladv.com

stampa  
Formagrafica

06/2018